





TECHNICAL DATA		
CHEMICAL BASE		One-part polyurethane
COLOUR		White Grey Black
SKINNING TIME		approx 60 minutes @ 23°C/50%RH
HARDNESS SHORE A		40 Approx
CURE TIME		2-3mm per hour @23°C/50%RH
CURE MECHANISM		Moisture curing
APPLICATION TEMPERATURE		+5 to +35°C
SERVICE TEMPERATURE		-30 to +80°C
SPECIFIC GRAVITY		Approx 1.18 Kg/l @ 20°C
SLUMP RESISTANCE		Excellent up to 25mm joints
MOVEMENT ACCOMMODATION		± 20%
ELONGATION AT BREAK		Approx 600%
MODULUS@100%		0.4 MPa
SHELF LIFE		9 months when stored in dry conditions between +5 to +25°C

**HEALTH AND SAFETY** • Refer to the relevant Material Safety Data Sheet (MSDS).

**PACKAGING** • Available in 310ml rigid cartridge. Other packs available on request.

**LEGAL NOTICE**

The data contained within this Technical Data Sheet is furnished for information only and is believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the customer to determine the products suitability for use. Delta Adhesives Limited accepts no liability arising out of the use of this information or the product described herein.

Delta Adhesives Limited, Units 39-40 Claycliffe Business Park,  
Cannon Way, Barugh Green, Barnsley, South Yorkshire, S75 1JU,  
Tel: +44 (0) 1226 381 571 email: sales@delta-adhesives.co.uk

