

Screw Grade Adhesive

Product Code: D44

CURING PROPERTIES

Handling Cure Time	20 minutes
Functional Cure Time	1 - 3 hours
Full Cure Time	24 hours
Breakaway Torque	6 N.m; 53 lb.in

KEY BENEFITS

-  Fast Curing
-  Designed for Small Fasteners
-  Low Strength Locking
-  Heat Resistant
-  Anti-Vibration



PRODUCT OVERVIEW

Delta 44 is a low-strength, thixotropic anaerobic threadlocker designed for bonding and sealing threaded assemblies and retaining cylindrical components. It is ideal for small screws and fasteners requiring secure locking with easy disassembly. The product provides excellent resistance to heat, vibration, oils, water, gases, hydrocarbons, and a wide range of chemicals.

TECHNICAL PROPERTIES

PROPERTY	VALUE
Composition	Methacrylate Ester
Colour	Purple
Viscosity	1000 cps at 25°C
Specific Gravity	1.05
Flash Point	>100°C
Temperature Range	-55°C to 150°C

APPLICATIONS

 Thread Locking Small Screws

 Small Diameter Fasteners

 Fasteners Exposed to Vibration

CHEMICAL RESISTANCE

CHEMICAL	TEMP	500 Hours	1000 Hours
Acetone	22°C	100%	80%
Ethanol	22°C	100%	100%
Motor Oil (125°C)	125°C	100%	100%
Gasoline	22°C	100%	100%
Break Fluid	22°C	100%	100%
Water/Glycol (87°C)	87°C	90%	85%

INSTRUCTIONS FOR USE

- 1. Prepare surfaces** - Ensure all parts are clean, dry, and free from oil, grease, or other contaminants before application.
- 2. Apply adhesive** - Apply Delta 44 directly to the threads in sufficient quantity to fill the gaps. The product performs best in thin bond gaps.
- 3. Assemble components** - Assemble and tighten parts as required. The formulation provides controlled friction and consistent torque/tension during assembly.

STORAGE

Anaerobic adhesives shall be ideally stored in a cool, dry place in unopened containers at a room temperature between 5 °C and 25 °C. Please do not return any unused material in its original container.

HEALTH AND SAFETY

- Classification: Xi irritant
- Keep out of reach of children
- Keep away from face and eyes
- Shelf Life: 2 Years

LEGAL NOTE

The data contained within this Technical Data Sheet is furnished for information only and is believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the customer to determine the products suitability for use. Delta Adhesives Limited accepts no liability arising out of the use of this information or the products described herein.